

# TECHNICAL DATA SHEET



Validation date: 11/07/2017

ISO 9001



## CUSTOMIZED MANUFACTURING 1PURX35MAT/LCW

## CONVEYOR BELT TPU BLUE

Complies with FDA and EU regulations for conveying of foodstuff

### CONSTRUCTION

<b>1</b>	1-ply polyester fabric
<b>PUR</b>	TPU polyurethan
<b>X</b>	Colour : blue RAL 5015
<b>35</b>	Top cover thickness : 0,35 mm
<b>MAT</b>	Mat finish
<b>LC</b>	115N/mm fabric, rigid in weft, antistatic
<b>W</b>	Impregnated backside

### MAIN TECHNICAL DATA


<b>Top cover:</b>	hardness: 85 Sh.A	surface: mat, smooth
<b>Total thickness:</b>	0,95 mm	$\pm 0,1$ mm per ply
<b>Weight per m<sup>2</sup>:</b>	1 050 g	$\pm 10\%$
<b>Friction Coefficient on steel slider bed:</b>	0,20	$\pm 20\%$
<b>Manufacturing width:</b>	2 000 mm	
<b>Temperatures:</b>		
* Product temperature:	-40°C	to +90°C
* Ambient temperature:	-25°C	to +60°C
<b>Type of support:</b>	Slider bed	

### MECHANICAL DATA

Tolerances: +20% -10%

<b>Breaking load:</b>	90 N/mm
<b>Load for 1% extension:</b>	7 N/mm
<b>Maximum working tension:</b>	10 N/mm

### Pulley diameters:



These values are not linked to the requested Ø to pull the belt to rotation.

Ambient temperature: from 0°C to +8°C: add +50%  
from 0°C to -25°C: add +100%

### ENDLESS JOINTINGS

Top heating plate:	135°C $\pm 10^\circ$ C
Bottom heating plate:	145°C $\pm 10^\circ$ C
Time:	0 mn $\pm 1$ mn
Pressure:	1,5 bar $\pm 0,5$ bar
Additional material (powder or film):	none

These recommendations may vary according to the equipment used and press heating system.

### Splicing methods to be used:

DS (finger joint)



**Fasteners:** None

**Accessories that may be fitted on this belt:** None

These data are subject to modification. Please make sure of their validity.  
REVEYRON S.A. should not be held responsible when the data sheet used is not valid anymore.

**reveyron S.A.**

247, route du Mas Rillier, Les Echets - 01700 MIRIBEL - France

Tél.: +33 (0)4 78 91 81 01

Fax: +33 (0)4 78 91 05 09

[www.reveyron.com](http://www.reveyron.com)

E.mail: [info@reveyron.fr](mailto:info@reveyron.fr)