TECHNICAL DATA SHEET



CUSTOMIZED MANUFACTURING 2PURX40/LCW

CONVEYOR BELT TPU BLUE

Complies with FDA and EU regulations for conveying of foodstuff

CONSTRUCTION

2-ply polyester fabric PUR TPU polyurethan

Colour: blue RAL 5015 X Top cover thickness: 0,40 mm 40

115N/mm fabric, rigid in weft, antistatic LC

Impregnated backside W

MAIN TECHNICAL DATA

Top cover: hardness: 85 Sh.A surface: mat, smooth

Total thickness: 1,70 mm \pm 0,1 mm per ply

Weight per m2: 2 100 g ± 10% ± 20% Friction Coefficient on steel slider bed: 0,20

Manufacturing width: 2 000 mm

Temperatures:

-40°C to +90°C * Product temperature: -25°C to +60°C * Ambient temperature:

Slider bed Type of support:

Tolerances: +20% -10% MECHANICAL DATA

170 N/mm **Breaking load:** 12 N/mm Load for 1% extension: 20 N/mm Maximum working tension:

Pulley diameters: (recommended as a minimum with a 20°C ambient temperature)

Minimum drive and tension: Ø 30 mm

Minimum reverse flexing: Ø 50 mm

These values are not linked to the requested Ø to pull the belt to

rotation.

from 0°C to +8°C: add +50% Ambient temperature:

from 0°C to -25°C: add +100%

ENDLESS JOINTINGS

Top heating plate: 160°C ± 10°C Bottom heating plate: 155°C ± 10°C Time: 2 mn ± 1 mn Pressure: 2,0 bar \pm 0,5 bar

Additional material (powder or film): none

These recommendations may vary according to the equipment used and press heating system.

Splicing methods to be used:


DS (finger joint)



PE (overlap joint)



DS/DEC (double finger joint)



Fasteners: Minibelt-A, Minibelt-I, Secura01,

Securi-G2, Securinox-1, Agrafe-plast

Accessories that may be fitted on this belt:

Except for some cases, this belt can b fitted out with: guiding profiles, cleats

sidewalls

These data are subject to modification. Please make sure of their validity. REVEYRON S.A. should not be held responsible when the data sheet used is not valid anymore.

247, route du Mas Rillier, Les Echets - 01700 MIRIBEL - France

E.mail: info@reveyron.fr

reveyron S.A.

Tél.: +33 (0)4 78 91 81 01

Fax: +33 (0)4 78 91 05 09

www.reveyron.com