TECHNICAL DATA SHEET



Validation date: 27/05/2013

STANDARD RANGE 1PURX60HR/LCW

CONVEYOR BELT TPU BLUE

Complies with FDA and EU regulations for conveying of foodstuff

CONSTRUCTION

1 1-ply polyester fabric PUR TPU polyurethan

X Colour : blue RAL 501560 Top cover thickness : 0,60 mm

HR "Rice grain" positive pattern, easy to cleanLC 115 N/mm fabric, rigid in weft, antistatic

W Impregnated backside

MAIN TECHNICAL DATA

Top cover: hardness: 92 Sh.A surface: [HR] "Rice grain" patter

Total thickness: 1,20 mm \pm 0,1 mm per ply

Weight per m²: 1 160 g \pm 10% Friction Coefficient on steel slider bed: 0,20 \pm 20%

Manufacturing width: 2 000 mm

Temperatures:

* Product temperature: -40°C to +90°C * Ambient temperature: -25°C to +60°C

Type of support: Slider bed

MECHANICAL DATA

Tolerances: +20% -10%

Breaking load:90N/mmLoad for 1% extension:7N/mmMaximum working tension:10N/mm

Pulley diameters: (recommended as a minimum with a 20°C ambient temperature)

ambient temperature

Minimum drive and tension: Ø 8 mm

Minimum reverse flexing: Ø 20 mm

These values are not linked to the requested \emptyset to pull the belt to

rotation.

Ambient temperature: from 0°C to +8°C: add +50%

from 0°C to -25°C: add +100%

ENDLESS JOINTINGS


Top heating plate: $180^{\circ}\text{C} \pm 10^{\circ}\text{C}$ Bottom heating plate: $150^{\circ}\text{C} \pm 10^{\circ}\text{C}$ Time: $2 \text{ mn} \pm 1 \text{ mn}$ Pressure: $2,0 \text{ bar } \pm 0,5 \text{ bar}$

Additional material (powder or film): none

These recommendations may vary according to the equipment used and press heating system.

Splicing methods to be used:

DS (finger joint)



Fasteners: None

Accessories that may None be fitted on this belt:

These data are subject to modification. Please make sure of their validity. REVEYRON S.A. should not be held responsible when the data sheet used is not valid anymore.

reveyron S.A.

247, route du Mas Rillier, Les Echets - 01700 MIRIBEL - France

Tél.: +33 (0)4 78 91 81 01 Fax: +33 (0)4 78 91 05 09 www.reveyron.com

E.mail: info@reveyron.fr