

# TECHNICAL DATA SHEET



ISO 9001



Validation date: 04/09/2017

## CUSTOMIZED MANUFACTURING 2PURI0/CW-AL

## CONVEYOR BELT TPU CLEAR

Complies with FDA and EU regulations for conveying of foodstuff

### CONSTRUCTION

<b>2</b>	2-ply polyester fabric
<b>PUR</b>	TPU polyurethan
<b>I</b>	Colour : clear
<b>0</b>	Food approved TPU impregnation
<b>C</b>	80N/mm fabric, rigid in weft, antistatic
<b>W</b>	Impregnated backside

### MAIN TECHNICAL DATA

<b>Top cover:</b>	surface: impregnated fabric
<b>Total thickness:</b>	1,10 mm $\pm$ 0,1 mm per ply
<b>Weight per m<sup>2</sup>:</b>	1 050 g $\pm$ 10%
<b>Friction Coefficient on steel slider bed:</b>	0,20 $\pm$ 20%
<b>Manufacturing width:</b>	2 000 mm
<b>Temperatures:</b>	
* Product temperature:	-40°C to +90°C
* Ambient temperature:	-25°C to +60°C
<b>Type of support:</b>	Slider bed


### MECHANICAL DATA

Tolerances: +20% -10%

<b>Breaking load:</b>	120 N/mm
<b>Load for 1% extension:</b>	9 N/mm
<b>Maximum working tension:</b>	15 N/mm

### Pulley diameters:

(recommended as a minimum with a 20°C ambient temperature)



These values are not linked to the requested Ø to pull the belt to rotation.

Ambient temperature: from 0°C to +8°C: add +50%  
from 0°C to -25°C: add +100%

### ENDLESS JOINTINGS

Top heating plate:	160°C $\pm$ 10°C
Bottom heating plate:	155°C $\pm$ 10°C
Time:	1 mn $\pm$ 1 mn
Pressure:	2,0 bar $\pm$ 0,5 bar
Additional material (powder or film):	none

These recommendations may vary according to the equipment used and press heating system.

### Splicing methods to be used:

DS (finger joint)



### Fasteners:

SL00 - AZ5 - SECURI-P1

### Accessories that may be fitted on this belt:

Except for some cases, this belt can be fitted out with longitudinal tracking profiles

These data are subject to modification. Please make sure of their validity.  
REVEYRON S.A. should not be held responsible when the data sheet used is not valid anymore.

**reveyron S.A.**

247, route du Mas Rillier, Les Echets - 01700 MIRIBEL - France

Tél.: +33 (0)4 78 91 81 01

Fax: +33 (0)4 78 91 05 09

[www.reveyron.com](http://www.reveyron.com)

E.mail: [info@reveyron.fr](mailto:info@reveyron.fr)