# TECHNICAL DATA SHEET





ISO 9001

#### **CUSTOMIZED MANUFACTURING CONVEYOR BELT TPU CLEAR** 2PURI30I/LW-1300

1,80 mm ± 0,1 mm per ply

±20%

Tolerances: +20% -10%

170 N/mm

12 N/mm

20 N/mm

2100 g ± 10%

-40°C to +90°C

-25°C to +60°C

0,20

1 300 mm

Slider bed

(recommended as a minimum with a 20°C

Minimum drive and tension:

ambient temperature)

Ø 25 mm

Minimum reverse flexing: Ø 50 mm

Complies with FDA and EU regulations for conveying of foodstuff

CONSTRUCTION

- 2-ply polyester fabric 2
- PUR TPU polyurethan
- Colour : clear L
- Top cover thickness : 0,30 mm 30
- Clear inner ply Т
- 125N/mm fabric, rigid in weft L
- Impregnated backside w

### MAIN TECHNICAL DATA

Friction Coefficient on steel slider bed:

**Total thickness:** 

Manufacturing width:

\* Product temperature:

\* Ambient temperature:

MECHANICAL DATA

Load for 1% extension:

Maximum working tension:

Weight per m<sup>2</sup>:

**Temperatures:** 

Type of support:

**Breaking load:** 

**Pulley diameters:** 

Top cover: hardness: 90 Sh.A surface: mat, smooth

# **ENDLESS JOINTINGS**

Top heating plate:	155°C <i>± 10</i> °C
Bottom heating plate:	145°C <i>± 10</i> °C
Time:	0 mn ± 1 mn
Pressure:	2,0 bar ± 0,5 bar
Additional material (powder or film):	none

These recommendations may vary according to the equipment used and press heating system.

### Splicing methods to be used:


DS (finger joint)



PE (overlap joint)



DS/DEC (double finger joint)



Fasteners:

Accessories that may be fitted on this belt:

MINIBELT - SL02 - AZ7 - SECURI-P3

Except for some cases, this belt can t fitted out with : thin guiding profiles an cleats

These values are not linked to the requested Ø to pull the belt to rotation.

Ambient temperature:

from 0°C to +8°C: add +50% from 0°C to -25°C: add +100%

These data are subject to modification. Please make sure of their validity. REVEYRON S.A. should not be held responsible when the data sheet used is not valid anymore.

## reveyron S.A.

247, route du Mas Rillier, Les Echets - 01700 MIRIBEL - France Fax: +33 (0)4 78 91 05 09

www.reveyron.com

E.mail: info@reveyron.fr

Tél.: +33 (0)4 78 91 81 01