TECHNICAL DATA SHEET



Validation date: 19/05/2009

STANDARD RANGE 3PURB170/FPS

CONVEYOR BELT TPU WHITE

Complies with FDA and EU regulations for conveying of foodstuff

CONSTRUCTION

3 3-ply polyester fabricPUR TPU polyurethanB Colour : white

170 Top cover thickness: 1,70 mm

FPS "Rice grain" positive pattern, easy to clean with sealed edges,

rigid fabric

MAIN TECHNICAL DATA

Top cover: hardness: 92 Sh.A surface: mat, smooth

Total thickness: 5,00 mm \pm 0,1 mm per ply

Weight per m²: $5\,800\,g$ $\pm\,10\%$ Friction Coefficient on steel slider bed: 0,50 $\pm\,20\%$

Manufacturing width: 1 500 mm

Temperatures:

* Product temperature: -40°C to +90°C * Ambient temperature: -25°C to +60°C

Type of support: Slider bed, rollers

MECHANICAL DATA

Tolerances: +20% -10%

Breaking load:300N/mmLoad for 1% extension:18N/mmMaximum working tension:36N/mm

Pulley diameters: (recommended as a minimum with a 20°C ambient temperature)

Minimum drive and tension: Ø 180 mm

Minimum reverse flexing: Ø 240 mm

These values are not linked to the requested \emptyset to pull the belt to

rotation.

Ambient temperature: from 0° to $+8^{\circ}$: add $+50^{\circ}$

from 0℃ to -25℃: add +100%

ENDLESS JOINTINGS

Top heating plate: $170^{\circ}\text{C} \pm 10^{\circ}\text{C}$ Bottom heating plate: $160^{\circ}\text{C} \pm 10^{\circ}\text{C}$ Time: $3 \text{ mn} \pm 1 \text{ mn}$ Pressure: $2,0 \text{ bar} \pm 0,5 \text{ bar}$

Additional material (powder or film): none

These recommendations may vary according to the equipment used and press heating system.

Splicing methods to be used:

DS (finger joint)



Fasteners: Sécura 03 - Airport - Gémini

Accessories that may

be fitted on this belt: Except for some cases, this belt

can be fitted out with : guiding profiles, cleats, sidewalls

These data are subject to modification. Please make sure of their validity.

REVEYRON S.A. should not be held responsible when the data sheet used is not valid anymore.

reveyron S.A.

247, route du Mas Rillier, Les Echets - 01700 MIRIBEL - France

Tél.: +33 (0)4 78 91 81 01 Fax: +33 (0)4 78 91 05 09 www.reveyron.com

E.mail: info@reveyron.fr