TECHNICAL DATA SHEET



ISO 9001

CUSTOMIZED MANUFACTURING CONVEYOR BELT TPU CLEAR 3PURX30H/5C

3,10 mm ± 0,1 mm per ply

± 20%

Tolerances: +20% -10%

200 N/mm 11 N/mm

20 N/mm

3600 g ± 10%

-40°C to +90°C

-25°C to +60°C

0,20

2 000 mm

Slider bed

(recommended as a minimum with a 20°C

Ø 120 mm

Minimum reverse flexing: Ø 160 mm

Minimum drive and tension:

ambient temperature)

CONSTRUCTION

- 3 3-ply polyester fabric
- PUR TPU polyurethan
- X Colour : blue RAL 5015

MAIN TECHNICAL DATA

Friction Coefficient on steel slider bed:

- 30 Top cover thickness : 0,30 mm
- H 92 ShA mat

Total thickness:

Manufacturing width:

* Product temperature:

* Ambient temperature:

MECHANICAL DATA

Load for 1% extension: Maximum working tension:

Weight per m²:

Temperatures:

Type of support:

Breaking load:

Pulley diameters:

5C 80N/mm fabric, extra rigid in weft, antistatic

Top cover: hardness: 93 Sh.A surface: mat, smooth

ENDLESS JOINTINGS

Top heating plate:	155°C ± 10°C
Bottom heating plate:	155°C ± <i>10</i> °C
Time:	2 mn ± <i>1 mn</i>
Pressure:	2,0 bar ± <i>0,5 bar</i>
Additional material (powder or film):	none

These recommendations may vary according to the equipment used and press heating system.

Splicing methods to be used:


DS (finger joint)



PE (overlap joint)



DS/DEC (double finger joint)




Airport - Gemini

Fasteners:

Accessories that may be fitted on this belt:

Except for some cases, this belt can t fitted out with : guiding profiles, cleats sidewalls



Ambient temperature:

from 0°C to +8°C: add +50% from 0°C to -25°C: add +100%

Æ

These data are subject to modification. Please make sure of their validity. REVEYRON S.A. should not be held responsible when the data sheet used is not valid anymore.

reveyron S.A.



Tél.: +33 (0)4 78 91 81 01

247 route du Mas Rillier, Les Echets - 01700 MIRIBEL - France Fax: +33 (0)4 78 91 05 09 www.reveyron.com

E.mail: info@reveyron.fr